



Product Information

www.miller-stephenson.com

TriboSys™ Fluorinated Synthetic Lubricant

Description

TriboSys™ Thin Film Lube contains Krytox™ GPL oils, which are packaged into convenient eight or fourteen ounce aerosols (MS-110XN). This packaging provides an easy solution for lubricating hard to reach places with pinpoint accuracy. The low surface tension of the solvent carries the oil into tight crevices. Also available with Krytox™ grease.

The PFPE Synthetic Oils, in addition to having a wide operating temperature range (-94°F to 550°F), are chemically inert, non-migrating, insoluble in hydrocarbons, water, steam and solvents. They have low vapor pressure and low outgassing characteristics. They are oxygen compatible, which makes it safe for oxygen service.

ADVANTAGES:

- Evaporates quickly.
- Compatible with most plastics, elastomers and metals.
- Contains no silicone.
- Chemical and thermal stability.
- Nonflammable.
- Non-ozone depleting chemicals.
- RoHS compliant

TYPICAL PROPERTIES OF KRYTOX™ GPL OILS*

Density**1.86 to 1.91g/ml @ 75°F/24°C
 1.52 to 1.60 g/ml @ 400°F/204°C
 15.5 to 16.0 lb/gal @ 75°F/24°C

Surface tension16 to 20 mN/m (dyn/cm) @ 79°F/26°C

Refractive index**1.296 to 1.301 nD25

*Viscosity may vary within +/-10%.

**Increases slightly with increasing molecular weight.

PROPERTIES OF SOLVENTS

Liquid density1.39 g/cc @ 77°F/25°C

Boiling point115°F/83°C

Vapor pressure285 mmHg @ 77°F/25°C

Flash pointNone

Ozone depletion0.00

VOC Content0 gms/l

Plastic Compatibility of the Solvents:

(Immersion: 15 Minutes at Room Temperature)

Polyethylene	Acetal
Polyphenylene Oxide, PPO	Epoxy
Polyester, PET,PBT	Liquid Crystal Polymer
Polyimide, PI,PEI,PAI	Phenolic
Polyetherketone, PEK	PTFE, ETFE
Polyaryletherketone, PEEK	CPVC, PVC
Polyarylsulfone	Ionomer
Polypropylene	Polysulfone
Polyphenylene Sulfide, PPS	Polystyrene
ABS	

Note: Test for compatibility before use.

Elastomer Compatibility of the Solvents:

(Immersion: 15 minutes at Room Temperature)

Buna N, NBR, Nitrile	Buna S, SBR, GRS
Butyl Rubber, IIR	Chlorosulfonated PE
EPM, EPDM	Polysulfide
Natural Rubber, Isoprene	Neoprene
Urethane	Viton™ B
Silicone	

Note: Test for compatibility before use.

Metal Compatibility of the Solvents:

(2 weeks at 212°F/100°C in sealed tubes)

Zinc ¹	Aluminum
Stainless Steel	Copper ¹
Brass ¹	

The solvent is not compatible with strong bases; therefore, contact with highly basic process materials is not recommended.

Krytox™ is a trademark of The Chemours Company FC, LLC

1602-9K

The recommendation made here with and the information set forth with respect to the performance or use of our products are believed, but not warranted to be accurate. The products discussed are sold without warranty, as to fitness or performance, express or implied and upon condition that purchasers shall make their own test to determine suitability of such products for their particular purposes. Likewise, statements concerning the possible uses of our products are not intended as recommendations to use our products in the infringement of any patent.