



Product Information

www.miller-stephenson.com

MS-475C / 477C Acrylic Conformal Coating

Description

Acrylic Conformal Coating offers superior toughness and abrasion resistance, excellent dielectric properties, fungal resistance, and moisture and environmental protection. Acrylic resin meets the requirements of MIL-I-46058C Type AR. It is solderable for ease of repair.

Allow 48 hours minimum to reach room temperature before using cans stored or received during cold weather.

Application

MS-475C will cover 6.4 sq. ft. at a 2 mil. thickness per 14 oz. aerosol can. MS-477C, the bulk liquid version of this product, is available in quarts and gallons for dip, brush, or spray application, and will cover 91 sq. ft. per gallon at a 2 mil. thickness.

Drying and curing of acrylic coating depends upon evaporation of the solvent. Air dry coated boards for 30 minutes at 77°F/25°C to remove solvents before curing in oven or applying additional coats.

NOTE: DO NOT SHAKE CAN AGGRESSIVELY; INVERT CAN AND PURGE AFTER EVERY USE. Valve and actuator clogging will occur if this is not performed.

Acrylic conformal coating can be removed with MS-114C or MS-115 Conformal Coating Strippers.

Cured Electrical Properties

Dielectric Strength (volts/mil)	2000
Dielectric Constant (10Hz)	2.29
Dissipation Factor 10 ⁵ Hz	0.012
Volume Resistivity (ohm/cm)	1.04x10 ¹⁶

Cured Physical Properties (per MIL-1-46058C)

Operating Temperature: -67°F/-55°C to 230°F/ 110°C

Appearance: No blistering, wrinkling, cracking or peeling of film or discoloration of printed conductors or substrate after thermal shock or moisture resistance testing.

Flexibility: No cracking or crazing of film in bending over a 1/8" diameter mandrel.

Fungus Resistance: Non-nutrient per ASTM G21.

Fluorescent when viewed with ultraviolet light. Miller-Stephenson offers urethane, acrylic and silicone conformal coatings available in aerosol and bulk liquid.

Safety Data Sheets (SDS) are available upon request.

1436-9K

The recommendation made here with and the information set forth with respect to the performance or use of our products are believed, but not warranted to be accurate. The products discussed are sold without warranty, as to fitness or performance, express or implied and upon condition that purchasers shall make their own test to determine suitability of such products for their particular purposes. Likewise, statements concerning the possible uses of our products are not intended as recommendations to use our products in the infringement of any patent.

For technical information call 800.992.2424 or 203.743.4447
For product sales: CT 800.442.3424, CA 800.771.8161, IL 800.447.4866, Canada 800.307.2199
www.miller-stephenson.com