



Product Information

www.miller-stephenson.com

D0403B-10 Connector Lubricant

Description

By combining the superior lubricating qualities of Polyphenyl Ether with the cleaning power of a blend of solvents, Miller-Stephenson has created Connector Lubricant, a formulation that provides the most advanced total treatment for connectors.

D0403B-10 is 10% of Polyphenyl Ether (PPE) and used where temperatures exceed 257°F/125°C or where connectors are exposed to severe vibration. Also, connectors which are tin lead require treatment with higher concentration of lubricant.

VOC Content.....960 g/l

ADVANTAGES:

- Cleans, lubricates and protects multi-pin connectors
- Reduces insertion forces
- Greatly increases mating cycles (especially important where high pin counts are involved)
- Extends connector life by preventing corrosion and galling
- Removes contaminants and oxides.
- Is non-migrating-contains no silicones.
- Non ozone depleting
- Available with an UV (ultraviolet) indicator
- No interference in electrical continuity
- Nonflammable
- Available in multiple concentrations of PPE

The active ingredient of Connector Lubricant is a six (6) ring polyphenyl ether lubricant. This lubricant will help protect metal connector surfaces from excessive wear, when subjected to hundreds of mating cycles, thereby increasing the life of the connectors. It will also reduce insertion forces and provide corrosion protection in harsh environments.

Maximum Operating Temperatures

Estimated 20 year film life 230°F/110°C

Estimated 5 year film life 257°F/125°C

Note: Higher temperatures result in shorter film life.

Physical Properties: 6-ring Polyphenyl Ether

Surface Tension 54.2 dynes/cm

Evaporation Loss (ASTMD-972) 6.5 hrs.

400°F/204°C @ 760mm 0.04%

500°F/260°C @ 760mm 0.50%

500°F/260°C @ 140mm 1.10%

Oxidation – Corrosion wt.change of metals, mg
ASTM D 4636 (FTM 791-5307/5308) 600°F, 48h

Aluminum	0.04
Titanium	0.02
Steel	0.02
Copper	0.14
Silver	0.03

Thermal Stability 836°F/447°C

Low-Temperature Performance: Performs consistently over a wide range of low temperatures to -20°C.

Electrical Properties: 6-ring Polyphenyl Ether

Dielectric Constant	<u>60cy</u>	<u>1kc</u>	<u>10kc</u>	<u>100kc</u>
(@ 77°F/25°C)	4.54	4.54	4.55	4.53

Resistivity @ 77°F/25°C @ 500VDC 1.56 x 10¹⁴ohm-cm

Dielectric Strength 43 Kv

Safety Data Sheet is available upon request.

1344-6N

The recommendation made here with and the information set forth with respect to the performance or use of our products are believed, but not warranted to be accurate. The products discussed are sold without warranty, as to fitness or performance, express or implied and upon condition that purchasers shall make their own test to determine suitability of such products for their particular purposes. Likewise, statements concerning the possible uses of our products are not intended as recommendations to use our products in the infringement of any patent.