



Product Information

www.miller-stephenson.com

MS-115 Conformal Coating Stripper

Description

This stripper is specifically formulated for the removal of cured epoxy conformal coatings. It will strip most organic systems and some polyurethanes. It can also be used to dissolve Miller-Stephenson's silicone, urethane and acrylic conformal coatings and varnish from most types of electronic circuitry. It will not attack any metal surfaces. More aggressive than MS-114D. Compatibility with plastic materials should be tested before use.

ADVANTAGES:

- Nonflammable
- Fast, effective coating removal
- Safe for metal surfaces
- Contains no ozone depleting chemicals (ODC)
- RoHS compliant
- Available in quart and gallon containers

PHYSICAL PROPERTIES:

Color.....Clear to light yellow
Boiling point.....397°F/203°C
Odor.....Faint solvent
Density.....1.08g/cc @ 77°F/25°C
VOC Content.....540 gms/l
Flash point.....None
Form.....Liquid

Directions for Use:

To remove cured coatings:

Place object to be stripped in a tank and cover with liquid. The coating will begin to crack and/or be dissolved. The time will vary from minutes to hours depending on the coating thickness. After the coating is stripped, remove the part from the tank and flush with alcohol.

MS-115 is very volatile. Therefore, it is necessary to keep it in a closed container when soaking. Use in a well-ventilated area.

Safety Data Sheet (SDS) is available upon request.

1461-4N

The recommendation made here with and the information set forth with respect to the performance or use of our products are believed, but not warranted to be accurate. The products discussed are sold without warranty, as to fitness or performance, express or implied and upon condition that purchasers shall make their own test to determine suitability of such products for their particular purposes. Likewise, statements concerning the possible uses of our products are not intended as recommendations to use our products in the infringement of any patent.

For technical information call 800.992.2424 or 203.743.4447
For product sales: CT 800.442.3424, CA 800.771.8161, IL 800.447.4866, Canada 800.307.2199
www.miller-stephenson.com

Miller-Stephenson logo is a trademark of Miller-Stephenson Chemical Company Inc