



Product Information

www.miller-stephenson.com

MS-452N Protective Varnish Coating

Description:

MS-452N, Protective Varnish is designed for adverse environmental conditions. It offers excellent moisture, oil, chemical, and fungal resistance with good flexibility. It also provides electrical insulation to increase the reliability of printed circuit boards.

It dries to a tough, flexible film. Its moisture and fungus resistant properties make it ideal for use on stators, transformers, field coils, printed circuits, completed electric assemblies, junction boxes and cables.

Application:

MS-452N can be applied by dipping, brushing or spraying. For spraying applications, it is usually thinned 20-25% by weight with Xylene. The resin dries in 30 minutes and is fully cured in 24 hours.

The protective varnish can be removed with MS-114D or MS-115 Conformal Coating Strippers.

Cured Electrical Properties

Dielectric Strength (volts/mil) DRY	1800
Dielectric Strength (volts/mil) WET	1200

Cured Physical Properties

Resistance:

Water	Excellent
Acid (10% Sulfuric Acid)	Excellent
Alkali	Excellent
Salt Water	Excellent
Oil, ASTM D-115	PASS
Corrosive effect on Copper	None

Physical Properties

Highest Operating Temperature	331°F /155°C
Fungus Resistance	Pass
Fluorescent	Under UV light

Miller-Stephenson offers urethane, acrylic and silicone conformal coatings available in aerosol and bulk liquid.

Safety Data Sheet (SDS) is available upon request.

1244-9L

The recommendation made here with and the information set forth with respect to the performance or use of our products are believed, but not warranted to be accurate. The products discussed are sold without warranty, as to fitness or performance, express or implied and upon condition that purchasers shall make their own test to determine suitability of such products for their particular purposes. Likewise, statements concerning the possible uses of our products are not intended as recommendations to use our products in the infringement of any patent.