



# Product Information

www.miller-stephenson.com

## SolvSys™ MS-550N / 552N Cleaning Solvent & Flux Remover

### Description:

A nonflammable, cleaning solvent and flux remover for critical cleaning of electronic components, circuits, precision instruments, electrical contacts, relays, and switching devices. Well suited for cleaning oils, flux and particulate matter from complex assemblies. Evaporates quickly and leaves no residue. It replaces HCFC-225 in many applications.

### Advantages:

- Evaporates quickly
- Leaves no residue
- Nonflammable
- Non-ozone depleting
- RoHS2 and RoHS3 Compliant

### Properties of Solvent:

Boiling Point.....122°F/50°C  
 Flash Point.....None  
 Liquid Density.....1.35 g/ml @ 77°F/25°C  
 Ozone Depletion.....0.00  
 VOC Content of MS-550N.....928 g/l  
 VOC Content of MS-552N.....928 g/l

### Plastic Compatibility:

(Immersion: 15 minutes at Room Temperature)

- |                 |                        |
|-----------------|------------------------|
| • Acetal        | • Polyethylene         |
| • Polypropylene | • Polyester, PBT, PET  |
| • PEK, PEEK     | • Epoxy-Phenolics      |
| • Polyimides    | • Polyvinylchloride    |
| • PTFE          | • Liq. Crystal Polymer |

**NOTE:** Acrylic, ABS, and polycarbonate, if under stress, may show slight cracking or crazing damage. Test for compatibility before use.

### Elastomer Capability:

(Immersion: 15 mins at Room Temperature)

- |                       |                  |
|-----------------------|------------------|
| • Butyl Rubber        | • Natural Rubber |
| • Polysulfide         | • EPDM           |
| • Buna S              | • Buna N         |
| • Neoprene            | • Urethane       |
| • Chlorosulfonated PE | • Silicone       |
| • Viton™              |                  |

**NOTE:** Elastomer swelling and shrinking will, in most cases, revert to within a few percent of original size after air drying. Swell, shrinkage, and extractables are strongly affected by the compounding agents, plasticizers, and curing used in the manufacture of the elastomers. Test for compatibility before use.

### Metal Compatibility:

(Immersion: 2 weeks at 99°F/37°C)

- Aluminum
- Copper
- Iron

**Note:** Test for compatibility before use.

**Safety Data Sheets (SDS) are available upon request**

Viton™ is a trademark of The Chemours Company FC, LLC.

**Disclaimer:** The manufacturer shall not be liable for any injury, loss or damage, direct or consequential, arising out of the use or inability to use this product. User shall determine the suitability of the product for his intended use and user assumes all risk and liability in connection therewith.

1596-9N

For technical information call 800.992.2424 or 203.743.4447  
 For product sales: CT 800.442.3424, CA 800.771.8161, IL 800.447.4866, Canada 800.307.2199  
[www.miller-stephenson.com](http://www.miller-stephenson.com)

Miller-Stephenson logo and SolvSys™ are trademarks of Miller-Stephenson Chemical Company Inc