



Product Information

www.miller-stephenson.com

MS-765 / 767 Cleaning Agent

Description

MS-765 and MS-767 Cleaning Agent is an azeotrope of a hydrofluorocarbon fluid with methanol. This product offers solvency for polar soils, while maintaining excellent compatibility with most plastics and metals. It is ideally suited for precision and specialty cleaning and rinsing. Typical applications include removing particulates, fingerprints and ionic salts, from metal, plastic and glass parts.

ADVANTAGES

- Evaporates quickly
- Leaves no residue
- Nonflammable
- Compatible with most plastics, elastomers and metals
- Non ozone-depleting
- RoHS Compliant

MS-767 (bulk): Vapor degreasing is suggested for optimum cleaning effectiveness. Modern vapor containment technology is recommended for both batch and in-line equipment. These systems have higher freeboard and a secondary set of low temperature (-20°F/-29°C) condenser coils to greatly reduce vapor losses.

PHYSICAL PROPERTIES

(Measured @ 77°F, unless otherwise noted)

Liquid density.....	1.49 g/cc
Boiling point.....	118°F/48°C
Vapor pressure.....	298 mmHg
Surface tension.....	14.1dyn/cm
Ozone Depletion.....	0.00
VOC Content	
Aerosol.....	58 gms / l
Bulk.....	89 gms / l

PLASTIC COMPATIBILITY

(Immersion: 15 Minutes at Room Temperature)

Polyethylene	Acetal
Polyphenylene Oxide, PPO	Epoxy
Polyester, PET,PBT	Polycarbonate
Polyimide, PI,PEI,PAI	Phenolic
Polyetherketone, PEK	PTFE, ETFE
Polyaryletherketone, PEEK	CPVC, PVC
Polyarylsulfone	Ionomer
Polypropylene	Polysulfone
Polyphenylene Sulfide, PPS	Polystyrene
ABS	Acrylic

ELASTOMER COMPATIBILITY

(Immersion: 15 Minutes at Room Temperature)

Buna N, NBR, Nitrile	Buna S, SBR, GRS
Butyl Rubber, IIR	Chlorosulfonated PE
EPM, EPDM	Polysulfide
Natural Rubber, Isoprene	Neoprene
Urethane	Viton™ B
Silicone	

METAL COMPATIBILITY

(2 weeks at 212°F/100°C in sealed tubes)

Zinc	Aluminum
Stainless Steel	Brass
Copper	

Large amounts of water may extract alcohol and affect cleaning performance. Therefore, to reduce alcohol loss, use desiccant dryers rather than water separators in the condensate return line. Contact with highly basic process materials, pH 10 or above, is not recommended.

Note: Test for compatibility before use.

Safety Data Sheets (SDS) are available upon request.

Viton™ is a trademark of The Chemours Company FC, LLC.

1343-12K

The recommendation made here with and the information set forth with respect to the performance or use of our products are believed, but not warranted to be accurate. The products discussed are sold without warranty, as to fitness or performance, express or implied and upon condition that purchasers shall make their own test to determine suitability of such products for their particular purposes. Likewise, statements concerning the possible uses of our products are not intended as recommendations to use our products in the infringement of any patent

For technical information call 800.992.2424 or 203.743.4447
For product sales: CT 800.442.3424, CA 800.771.8161, IL 800.447.4866, Canada 800.307.2199
www.miller-stephenson.com