



Product Information

www.miller-stephenson.com

TriboSys™ Advanced Medical Lubricants

MS-3140MD Oil
MS-3240MD Grease

TriboSys™ perfluorinated oil and grease provides superior quality lubrication under extreme conditions in comparison to hydrocarbon and silicone alternatives. TriboSys™ is the lubricant of choice for medical performance and complete reliability.

Biocompatible ISO: 10993

Key Benefits & Characteristics

- Nonflammable • Non-Nutrient Lubrication • Oxygen Safe • Odorless and Colorless • Chemically Inert
- Withstands all sterilization techniques • Extreme Temperature Stability

Chemical Resistance	Biocompatibility	Sterilization
TriboSys™ is a clear, colorless, fluorinated synthetic oil or grease that is nonreactive, nonflammable, safe in chemical and oxygen service and is long-lasting.	Physical, chemical and toxicological testing was done according to ISO 10993 and/or USP Class VI standards to determine the biocompatibility of our grease and oil grades.	TriboSys™ withstands all forms of hospital sterilization with no migration or lubrication degradation.

APPLICATIONS & TECHNICAL DATA

Common Uses

- Single and Multi-Use Surgical Device Housings
- O-Rings
- Anesthesia Machine Parts
- Oxygen Valves
- Monitoring Devices: Housings, Covers, Pumps
- Renal Care: Blood Filter Housings, Pumps
- Fluid & Drug Delivery: Syringes, Stopcocks, Luers, ect.
- Diabetes Management: Glucose Meters, Infusion Pumps, Insulin Pens

Typical Requirements

- Sterilization Stability: Gamma or electron beam (e-beam) radiation; ethylene oxide (EtO) or steam autoclave
- Dimensional Stability
- Chemical Stability
- Durability/Impact Resistance
- Biocompatible Tested Grades

For technical information call 800.992.2424 or 203.743.4447
For product sales: CT 800.442.3424, CA 800.771.8161, IL 800.447.4866, Canada 800.307.2199
www.miller-stephenson.com

Typical Properties

Oil	MS-3140MD
Grease	MS-3240MD
ISO Grade of Oil ¹	68
Estimated Useful Range ²	
°C	-51-179
°F	-60-355
Oil Viscosity, cSt	
20°C (68°F)	177
40°C (104°F)	60
100°C (212°F)	8.4
204°C (400°F)	-
260°C (500°F)	-
Oil Viscosity Index	111
Oil Pour Point	
°C	-51
°F	-60
Oil Density, g/ml	
0°C (32°F)	1.93
100°C (212°F)	1.75
Maximum Oil Volatility, ASTM D2595	
% in 22 hr.	
121°C (250°F)	3
204°C (400°F)	-
Oil Separation from Grease, ASTM D6184 wt loss, % in 30 hr	
99°C (210°F)	5
204°C (400°F)	-

This table gives typical properties (not specifications) based on historical production performance. Viscosity may vary within ±10%

¹Approximate

²Based on pour point and where evaporation is approximately 10%.

millersstephenson logo and TriboSys™ are trademarks of millersstephenson chemical company inc.

1656-3M

The recommendation made here with and the information set forth with respect to the performance or use of our products are believed, but not warranted to be accurate. The products discussed are sold without warranty, as to fitness or performance, express or implied and upon condition that purchasers shall make their own test to determine suitability of such products for their particular purposes. Likewise, statements concerning the possible uses of our products are not intended as recommendations to use our products in the infringement of any patent.